

: . .  
: /

## Properties

### Physical

Specific Gravity	ASTM D792	23	-	
Mold Shrinkage	NPK Method	-	%	0.5~0.7

### Mechanical

Tensile Strength at yield	ASTM D638	1/8", 5mm/min	kg/cm <sup>2</sup>	450
Elongation at break	ASTM D638	1/8", 5mm/min	%	5
Flexural Strength	ASTM D790	1/8", 1.3mm/min	kg/cm <sup>2</sup>	800
Flexural Modulus	ASTM D790	1/8", 1.3mm/min	kg/cm <sup>2</sup>	42,000
IZOD (Notched) IZOD Impact Strength	ASTM D256	1/4", 23	kgcm/cm	4

### Thermal

Melt Flow Index	ASTM D1238	230 , 2.16kg	g/10min	5
Heat Deflection Temperature	ASTM D648	1/4", 4.6kgf/cm <sup>2</sup> 1/4", 18.5kgf/cm <sup>2</sup>		155

Data  
The listed values should be used for referential purpose only.