

: . .
: /

Properties

Physical

Specific Gravity	ASTM D792	23	-
Mold Shrinkage	NPK Method	-	%

Mechanical

Tensile Strength at yield	ASTM D638	1/8", 5mm/min	kg/cm ²	700
Elongation at break	ASTM D638	1/8", 5mm/min	%	10
Flexural Strength	ASTM D790	1/8", 1.3mm/min	kg/cm ²	1,200
Flexural Modulus	ASTM D790	1/8", 1.3mm/min	kg/cm ²	35,000
IZOD (Notched) IZOD Impact Strength	ASTM D256	1/4", 23	kgcm/cm	9

Thermal

Melt Flow Index	ASTM D1238	300 , 1.2kg	g/10min	15
Heat Deflection Temperature	ASTM D648	1/4", 4.6kgf/cm ² 1/4", 18.5kgf/cm ²		140

Data
The listed values should be used for referential purpose only.